



## XTRAKOTE SEALER RC

advanced coating systems



### CLEAR TWO COMPONENT RAPID CURE CYCLOALIPHATIC SEAL

#### GENERAL PRODUCT DESCRIPTION

XtraKote Sealer RC (rapid cure) is a two component, 100% solids cycloaliphatic epoxy. It serves as a decorative, high performance, seamless overlayment floor and cove base system. The beauty of XtraKote Sealer RC comes from its unique water-clear cycloaliphatic epoxy. XtraKote Sealer RC cures in four hours at 70° F (half the time of conventional epoxy systems). Its epoxy chemistry provides excellent bonding characteristics. It can be applied as a single broadcast (45-50 mil) coating system, a double broadcast (100-125 mil) or over a CoreKote HB (1/4") or other high build system. Its design features provide for the highest industrial demands. Advantages:

- Essentially odorless
- Self-priming
- VOC Compliant- 100% Solids
- High gloss
- Anti-slip and Texture control - Flexibility of smooth under equipment and textured in walkways
- Withstands heavy traffic
- Chemical resistant
- Able to be applied over damp concrete
- No amine blush
- Can be applied over ten day old concrete

#### PRODUCT DATA

Volumetric Ratio:	2 to 1
Solids:	100%
Coverage:	Topcoat - 100-200 S/F per gal.
Application Temperature:	65-90°F and 5° above the dew point
Thinning:	Not required
Pot Life:	10-15 minutes
Working time on floor:	15-20 minutes
Cure Time:	4-6 hours (walking) 18 hours (traffic)
Critical recoat time:	24 hours
Shelf life:	12 months
USDA Food and Beverage:	Meets requirements

#### PHYSICAL PROPERTIES

PROPERTY	VALUE	REFERENCE
Compressive Strength	18,800 psi	ASTM C 579
Flexural Strength	2,270 psi	ASTM D 790
Tensile Strength	1,560 psi	ASTM D 638
Bond to Concrete	350 psi concrete fails at this point	ASTM D 4541
Coefficient of Friction	0.6 minimum	ASTM D 2047
Taber Abrasion	59 mgs	ASTM D 4060 CS 17 Wheels
Flammability	Self-extinguishing	ASTM D 635
Hardness, Shore D	82	ASTM D 2240
Flash Point	>200°F	ASTM D 93

#### INDUSTRIAL APPLICATIONS

The uniqueness and universality of its chemistry allows XtraKote Sealer RC to be used in the following applications:

- Pharmaceutical
- Laboratories
- Food Preparation
- Dairies
- Restrooms and Showers
- Kitchens
- Hospitals
- Correctional Facilities
- Clean rooms
- Animal Care Facilities
- Showrooms
- Schools

#### COLORS

XtraKote Sealer RC is clear.

# XTRAKOTE SEALER RC

## CONCRETE PREPARATION

Before the coating is applied, the concrete must be:

- Clean – Contaminants removed
- Profiled – Surface etched
- Sound – Cracks repaired

Mechanical methods are preferred for preparing concrete prior to coating application. Shot-blasting, diamond grinding, scarifying, and scabbling are all acceptable methods. The concrete profile should approximate 60-80 grit sandpaper after preparation.

## PATCHING

Voids, cracks, and imperfections will be seen in finished coating if the concrete is not patched correctly. Patch concrete with Petra Patch. After the patching material has cured, diamond grind patch the concrete. If a non-Petra patching material is used, make sure that it is a two-part epoxy patch. Always test unproven products by applying patch material first, then Petra coating system next. Check to see if bonding is firm.

## MIXING

The ratio of XtraKote Sealer RC is 2 to 1. That is, two parts of A - resin, to one part of B - hardener. Generally, three mixed gallons is ideal for application. Mix the following with a drill and jiffler mixer.

1. Part A does not require pre-mixing. If using the 15 gallon kit, pour out 2 gallons into an empty 5 gallon bucket which then becomes the mixing bucket. (The three gallon kit allows the Part A bucket to be used as the complete mixing bucket, since the Part A comes in a three and a half gallon bucket.)
2. Add one gallon of part B and mix for 60-90 seconds.
3. Immediately apply to the floor. XtraKote Sealer RC in mass has a short pot life of approximately 15-20 minutes. Once poured out on the floor, 20-30 minutes of working time can generally be expected.

## APPLICATION PROCESS

XtraKote Sealer RC for a nominal 16 mil topcoat is applied as follows:

1. Always apply in descending temperatures. Concrete is porous and traps air. In ascending temperatures (generally mornings), the air expands and can cause out gassing in the coating. It is safer to apply coatings in the late afternoon, especially for exterior applications. Optimum ambient temperature should be between 65-90°F and five degrees above the dew point during application.
2. Mix three gallons of resin using above mixing instructions.
3. Apply approximately 100 S/F per gallon and spread by using a window squeegee on a pole pulling XtraKote Sealer RC over substrate. Lastly, using a 3/8" non-shedding phenolic (plastic) core paint roller, roll coating forwards and backwards. Then roll from left to right.

## PRODUCT LIMITATION

Ground level concrete slabs emit moisture vapor. The allowable moisture emissions for concrete is 3 lbs. 1000 S/F over a twenty-four hour period. If moisture is above this level, then blistering and delamination of coating may occur. A calcium chloride test should be performed to determine concrete moisture level. If moisture levels exceed the 3 lb. limit, a concrete moisture vapor control system should be used first before applying coating system. Please contact Petra technical department for approved systems.

Coating systems are susceptible to cracking if the concrete moves or separates below the coating. Hence, joint and crack treatment should be reviewed prior to coating application. As a general rule, control joints (saw cuts) and random cracks should be saw cut or chased first then filled with Petra Patch or similar approved hard epoxy product. Construction joints (two slabs which meet and hence move) should be treated. After the coating has been applied and cured, saw cut through the coating over construction joints.

## PACKAGING

XtraKote Sealer RC is available in two different kit sizes:

	<u>Part A</u>	<u>Part B</u>
3 Gallon Kit	2 gal.	1 gal.
15 Gallon Kit	10 gal.	5 gal.

## CLEANUP

XtraKote Sealer RC, while in an unreacted state, may be cleaned up with water and degreaser. Isopropyl alcohol or acetone may be needed once the resin begins hardening. Lastly, a stronger solvent may be required if the resin is nearly set up.

## WARRANTY

Petra Polymers products are warranted for one year after date of application. Please refer to the Petra Polymer's Limited Material Warranty for additional clarification.

## SAFETY

Consult XtraKote Sealer RC material safety data sheet. Avoid XtraKote Sealer RC contact with skin. Some individuals may be allergic to epoxy.

Information expressed in this data sheet is correct to the best of our knowledge. The technical data sheet does not constitute a warranty, expressed or implied as to the performance of this product. The use and application of this product is beyond our control. Warranty and liability therefore is limited to the replacement only for defective materials. Technical information is subjected to change without cause.

XtraKote Sealer RC 2of 2

